

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁷ : C08L 23/08 // (C08L 23/08, 23:14)</p>	<p>A1</p>	<p>(11) International Publication Number: WO 00/02960 (43) International Publication Date: 20 January 2000 (20.01.00)</p>
<p>(21) International Application Number: PCT/EP99/04597 (22) International Filing Date: 2 July 1999 (02.07.99) (30) Priority Data: MI98A001547 7 July 1998 (07.07.98) IT (71) Applicant (for all designated States except US): MONTELL TECHNOLOGY COMPANY B.V. [NL/NL]; Hoeksteen 66, NL-2132 MS Hoofddorp (NL). (72) Inventors; and (75) Inventors/Applicants (for US only): CECCHIN, Giuliano [IT/IT]; Via Gelsomini, 50, I-44100 Ferrara (IT). COL- LINA, Gianni [IT/IT]; Via XXI Aprile 1945, 3, I-44044 Loc. Cassana (IT). COVEZZI, Massimo [IT/IT]; Via Renata di Francia, 40, I-44100 Ferrara (IT). CIARAFONI, Marco [IT/IT]; Via Risorgimento, 84, I-44100 Ferrara (IT). ANI- BALDI, Remo [IT/IT]; Via Aducco, 13, I-44100 Ferrara (IT). (74) Agent: GAVERINI, Gaetano; Montell Italia S.p.A., Intellec- tual Property Patents and Trademarks, Via Pergolesi, 25, I-20124 Milano (IT).</p>		<p>(81) Designated States: AU, BR, CA, CN, CZ, IN, JP, KR, MX, NO, RU, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published With international search report.</p>
<p>(54) Title: POLYETHYLENE COMPOSITIONS HAVING IMPROVED MECHANICAL PROPERTIES AND IMPROVED PROCESS- ABILITY IN THE MELTED STATE (57) Abstract Polyethylene composition comprising (percentages by weight): A) from 60 to 95 % of an LLDPE copolymer having a density from 0.905 to 0.935 g/cm³, $\overline{M}_w/\overline{M}_n$ values less than 4 and F/E ratio values from 10 to 20; B) from 5 to 40 % of one or more crystalline copolymers of propylene selected among defined copolymers of propylene with ethylene and/or higher alpha-olefins.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NI	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

"POLYETHYLENE COMPOSITIONS HAVING IMPROVED MECHANICAL PROPERTIES AND IMPROVED PROCESSABILITY IN THE MELTED STATE"

* * * * *

The present invention concerns polyethylene compositions comprising a linear low-density copolymer of ethylene (LLDPE) having a narrow distribution of molecular weights, and a crystalline copolymer of propylene.

The films obtainable from the said compositions possess an improved balance of mechanical properties and good optical properties.

Moreover, the aforesaid compositions are readily processable in the melted state, since they do not require large expenditures of energy in the machines used for their processing and do not cause high pressures at the head in the machines themselves.

The copolymer of ethylene used for the compositions of the present invention possesses a molecular weight distribution, in terms of the ratio between the weight-average molecular weight (\overline{M}_w) and the number-average molecular weight (\overline{M}_n), that is in terms of $\overline{M}_w/\overline{M}_n$, which is particularly narrow (corresponding to values of $\overline{M}_w/\overline{M}_n$ less than 4) and hence typical of the polyethylenes obtained with metallocene catalysts.

In that respect, the compositions of the present invention differ from the compositions described in published patent applications WO 93/03078 and WO 95/20009, in which the

LLDPE copolymer (which is mixed with a crystalline copolymer of propylene) is prepared with Ziegler-Natta catalysts and hence possesses values of $\overline{M}_w/\overline{M}_n$ typically greater than or equal to 4.

According to US patent 4,871,813, it is possible to prepare LLDPE copolymers having $\overline{M}_w/\overline{M}_n$ values less than 4 (from 2.5 to 6) even when the catalyst used is of the Ziegler-Natta type, however in the examples only an LLDPE copolymer having a $\overline{M}_w/\overline{M}_n$ value of 4 is used.

Also in the US patent cited the LLDPE copolymer is mixed with a copolymer of propylene, however the crystallinity of that copolymer of propylene is rather low, as is indicated by the low values of the enthalpy of fusion (less than or equal to 75 J/g) and, in particular, the degree of crystallinity (less than 35%).

The aforesaid documents show that by the addition of the copolymer of propylene to the LLDPE copolymer, polyethylene compositions having improved processability in the melted state, in the aforesaid sense, are obtained.

According to US patent 4,871,813, this effect is obtained without substantially changing the optical and mechanical properties of the film, compared to those of a film obtained from the pure LLDPE copolymer.

According to published patent application WO 95/20009, as well as improving the processability in the melted state, the addition of the crystalline copolymer of

propylene is capable of improving the resistance of the polyethylene film to impact and to tearing.

However, the mechanical properties of the compositions comprising an LLDPE copolymer obtained with Ziegler-Natta catalysts and a copolymer of propylene are inferior, in particular as regards the impact resistance (Dart Test), to those typical of an LLDPE copolymer obtained with metallocene catalysts.

The LLDPE copolymers obtained with metallocene catalysts in general show Dart Test values (measured on blown film of thickness 25 μm by the method described in the examples) higher than about 300 g.

Corresponding to the said high Dart Test values, such LLDPE copolymers also have satisfactory tear resistance values (Elmendorf), which generally vary in inverse proportion, i.e. they increase with decreasing Dart Test values, and excellent optical properties.

However, the LLDPE copolymers obtained with metallocene catalysts display unsatisfactory processability in the melted state, attributable to the narrow distribution of molecular weights that characterizes them.

Hence, it would be particularly desirable to obtain polyolefin compositions having the aforesaid high levels of impact resistance, with the best balance possible of impact resistance and tear resistance, improved optical properties, and good processability in the melted state.

In US patent 5,674,945, polyethylene compositions comprising an LLDPE copolymer obtained with metallocene catalysts and a copolymer of propylene having a density greater than or equal to 0.900 g/cm^3 are described.

In particular, in the examples a copolymer containing 0.2 mole% of butene and a copolymer containing 3.4 mole% of ethylene and 1.6 mole% of butene is used.

In both cases, the relative quantity of propylene copolymer in the polyethylene compositions is 10% by weight, and the transparency of the films obtained from such compositions is found to be substantially unchanged compared to the transparency of the films obtained from the corresponding LLDPE copolymers in the pure state.

Moreover, the films obtained from the aforesaid compositions show high tensile modulus values, superior to those of the films obtained from the corresponding LLDPE copolymers in the pure state, and high breaking strain values.

The technical problem consisting in obtaining excellent balances of impact resistance and tear resistance is not considered.

Polyethylene compositions have now been produced which fully satisfy the aforesaid requirements, thanks to an unusual and particularly favourable balance of mechanical and optical properties and processability in the melted state.

Hence, the present invention provides polyethylene compositions comprising (percentages by weight):

- A) from 60 to 95%, preferably from 60 to 90%, more preferably from 70 to 88%, of a copolymer of ethylene with an alpha-olefin $\text{CH}_2=\text{CHR}$, in which R is an alkyl radical containing from 1 to 18 atoms of carbon (LLDPE copolymer), the said copolymer having a density from 0.905 to 0.935 g/cm³, preferably from 0.910 to 0.930, more preferably from 0.915 to 0.925 g/cm³ (measured according to ASTM D 4883), $\overline{M}_w/\overline{M}_n$ values less than 4, preferably from 1.5 to 3.5, more preferably from 1.5 to 3 (measured by GPC, i.e. gel permeation chromatography) and values of melt flow rate F/E ratio from 10 to 20, preferably from 12 to 20 (measured according to ASTM D 1238);
- B) from 5 to 40%, preferably from 10 to 35%, more preferably from 12 to 30%, of one or more crystalline copolymers of propylene selected among (i) copolymers of propylene with ethylene containing from 3 to 8%, preferably from 4 to 6%, of ethylene; (ii) copolymers of propylene with one or more alpha-olefins $\text{CH}_2=\text{CHR}^I$, where R^I is an alkyl radical having from 2 to 8 carbon atoms or an aryl radical, containing from 6 to 25%, preferably from 8 to 20%, of alpha-olefins $\text{CH}_2=\text{CHR}^I$; (iii) copolymers of propylene with ethylene and one or more alpha-olefins $\text{CH}_2=\text{CHR}^I$, where R^I has the aforesaid meaning, containing from 0.1 to 8%, preferably from 0.5 to 5%, more preferably from 1 to 4%, of ethylene, and from 0.1 to 20%, preferably from 1 to 15%, more preferably from 2.5 to 15%, in particular from 2.5 to 10%,

of alpha-olefins $\text{CH}_2=\text{CHR}^I$, with the proviso that the total content of ethylene and alpha-olefins $\text{CH}_2=\text{CHR}^I$ in the copolymers (iii) is greater than or equal to 5%.

Optionally, in order to improve the optical properties, the compositions of the present invention can contain, in addition to the components A) and B), from 0.5 to 10%, preferably from 1 to 6%, by weight of an LDPE polyethylene (component C)), with respect to the total weight of A) + B) + C).

As seems clear from the foregoing description, polymers containing two or more types of comonomers are also included in the definition of copolymers.

The aforesaid compositions are generally characterized by Dart Test values greater than or equal to 300 g, preferably greater than or equal to 350 g, in particular between 300 and 800 g, preferably between 350 and 800 g (measured on blown film of thickness 25 μm by the method described in the examples).

Moreover, the compositions of the present invention show particularly high tear resistance values (Elmendorf), both as such and compared to the Dart Test values. Generally, such values are greater than or equal to 400 g (measured on blown film of thickness 25 μm by the method described in the examples) in the transverse direction (TD), in particular between 400 and 800 g, and greater than or equal to 200 g in the machine direction (MD), preferably greater than or equal

to 250 g, in particular between 200 and 500 g, preferably between 250 and 500 g.

Generally, the component A) of the compositions of the present invention has an ethylene content greater than or equal to 60% by weight, in particular from 60 to 99%, preferably greater than or equal to 70% by weight, in particular from 70 to 99%, more preferably greater than or equal to 80% by weight, in particular from 80 to 99%.

Examples of alpha-olefins $\text{CH}_2=\text{CHR}$ present in the component A) of the compositions of the present invention are propylene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene, 1-octene, 1-decene, 1-dodecene, 1-tetradecene, 1-hexadecene, 1-octadecene and 1-eicosene.

Preferred examples are 1-butene, 1-hexene and 1-octene.

Generally, the component A) has Melt Flow Rate E values (MFR E according to ASTM D 1238) from 0.1 to 100 g/10 min.

Moreover, the said component A) preferably has a content of fractions soluble in xylene at 25°C less than or equal to 5% by weight.


The DSC (Differential Scanning Calorimetry) trace of the said component A) preferably shows a single melting peak (typical of one crystalline phase); this peak is generally situated at a temperature greater than or equal to 100°C.

The LLDPE copolymers having the characteristics

quoted above for the component A) are known in the art and can be obtained by conventional polymerization processes (in gas phase, in suspension or in solution) using metallocene catalysts, optionally supported on solid supports (for example silica or porous polymeric supports).

The metallocene catalysts are prepared by combining a metallocene compound of a transition element generally selected in the groups IV B, V B or VI B of the periodic table of the elements, in particular titanium, zirconium or hafnium, and a co-catalyst, in particular an alumoxane.

The metallocene compound can be generally represented by the formula:




where Cp is a cyclopentadiene ring, which can also be part of polycyclic structures such as indenyl or fluorenyl, x is 1, 2 or 3, M is the aforesaid transition element, A and B, the same or different, are selected among hydrogen, halogens and alkyl groups, optionally containing heteroatoms, y and z are 0 or whole numbers greater than 0, with the proviso that the sum of x, y and z corresponds to the oxidation state of M.

Preferably, at least one of the cyclopentadiene rings Cp is substituted, in particular with alkyl substituents; moreover two cyclopentadiene rings can be joined together by bivalent groups, for example alkylene (polymethylene) or dialkylsilane groups.


Specific examples are the derivatives of

bis(cyclopentadienyl)zirconium dichloride having variously substituted cyclopentadiene rings.

The alumoxanes comprise the oligomeric linear compounds of formula:



and cyclic ones of formula:



where n varies for instance from 1 to 40, m from 3 to 40 and R is an alkyl group preferably containing from 1 to 8 atoms of carbon.

A specific example is methylalumoxane.

Alternatively to the alumoxanes, compounds capable of forming a metallocene alkyl cation can be used as co-catalysts.

Examples of such compounds are the compounds of formula Y^+Z^- , where Y^+ is a Brønsted acid, capable of donating a proton and of reacting irreversibly with a substituent A or B of the metallocene compound and Z^- is a compatible anion, which does not coordinate, which is capable of stabilizing the active catalytic species which originates from the reaction of the two compounds, and which is sufficiently labile to be able to be displaced by an olefinic substrate. Preferably the anion Z^- includes one or more atoms of boron, more preferably it is an anion of formula $BAr_4^{(-)}$ where the substituents Ar, the same or different, are aryl radicals such as phenyl, pentafluorophenyl and bis(trifluoromethyl)phenyl.

Particularly preferred is tetrakis-pentafluorenyl-borate. In addition, the compounds of the formula BAr_3 , where B is boron and the substituents Ar, the same or different, have the meaning described above, can advantageously be used.

Examples of the aforesaid catalysts and polymerization processes are described in the already cited US patent 5,647,945 and in published patent applications EP-A-129 368 and WO 94/26816.

Examples of alpha-olefins $CH_2=CHR^1$ present in the component B) of the compositions of the present invention are 1-butene, 1-pentene, 4-methylpentene-1, 1-hexene and 1-octene. 1-butene is preferred.

Generally, the component B) has Melt Flow Rate L values (MFR L according to ASTM D 1238) from 0.1 to 500 g/10 min, preferably from 1 to 50, more preferably from 6 to 25 g/10 min.

Preferably the said component B) has density values (measured according to ASTM D 4883) less than 0.9 g/cm^3 , in particular from 0.890 to 0.899, more preferably from 0.892 to 0.899.

Moreover, the said component B) preferably has the following characteristics:

- content of fraction insoluble in xylene at 25°C greater than 70% by weight, more preferably greater than or equal to 75%, in particular greater than or equal to 85% by weight;
- enthalpy of fusion (measured according to ASTM D 3418-82)

greater than 50 J/g, more preferably greater than or equal to 60 J/g, in particular greater than or equal to 70 J/g, for example from 75 to 95 J/g;

- melting point (measured according to ASTM D 3418-82) less than 140°C, more preferably from 120 to 140°C;
- $\overline{M}_w/\overline{M}_n$ values greater than 3.5, in particular from 3.5 to 15.

The crystalline copolymers of propylene having the characteristics quoted above for the component B) are known in the art, and can be obtained by conventional polymerization processes using stereospecific Ziegler-Natta catalysts supported on magnesium halides. Such catalysts contain, as an essential component, a solid catalytic component comprising a compound of titanium having at least one titanium-halogen bond and one electron-donor compound, both supported on a magnesium halide. As co-catalysts, an Al-alkyl compound and an electron-donor compound are generally used.

Catalysts having the aforesaid characteristics are for example described in US patent 4,399,054 and in European patent 45977.

The LDPE polymer (low density polyethylene) constituting the component C) of the compositions of the present invention is a homopolymer of ethylene or a copolymer of ethylene containing smaller quantities of comonomers, such as butyl acrylate, prepared by polymerization at high pressure using free radical initiators.

The density of the said LDPE polymer generally

varies from 0.910 to 0.925 g/cm³ (measured according to ASTM D 4883).

The MFR E values of the said LDPE polymer generally vary from 0.1 to 50 g/10 min, preferably from 0.3 to 20 g/10 min.

The LDPE polymers having the characteristics quoted above for the component C) are known in the art. Specific examples are the commercially available polymers with the trade names Escorene®, and Lupolen® (BASF).

In addition to the aforesaid components, the compositions of the present invention can contain other polymeric components, such as olefinic elastomers, in particular ethylene/propylene (EPR) or ethylene/propylene/diene (EPDM) elastomers, and additives commonly used in the art, such as stabilizers (in particular phenolic antioxidants and process stabilizers such as the organic phosphates), pigments, fillers, nucleating agents, slipping agents, lubricating and antistatic agents, flame retardants and plasticizers.

The compositions of the present invention can be prepared by processes of polymerization in two or more consecutive stages, using in at least one stage the metallocene catalysts described above for the preparation of the component A) and in at least one other stage the Ziegler-Natta catalysts described above for the preparation of the component B) and optionally adding the component C) by mixing

in the melted state.

Naturally, it is also possible to prepare the compositions of the present invention by mixing of the components A), B) and optionally C) in the melted state.

The processes of mixing in the melted state that can advantageously be used are of conventional type and are based on the use of mixing devices known in the art, such as single-screw and double-screw extruders.

In view of their ready processability in the melted state and their excellent mechanical properties, the compositions of the present invention are particularly suitable for the preparation of moulded articles in general, and in particular of film, monolayer or multilayer, whether cast or mono- or biaxially oriented, including blown films, in which at least one layer comprises the aforesaid compositions.

The processes for the preparation of blown film are well known in the art and comprise a stage of extrusion through a head with an annular aperture.

The product from this stage is a tubular extrudate which is then inflated with air, to obtain a tubular bubble which is cooled and collapsed to obtain the film.

The following examples are given in order to illustrate but not to limit the present invention.

For these examples, the following materials are used.

A) LLDPE Copolymer

Ethylene/1-hexene copolymer, containing 7.6% by weight of 1-hexene (determined by IR spectroscopy) and having the following characteristics:

Density (ATM D 4883):	0.9190 g/cm ³
$\overline{M}_w/\overline{M}_n$ (GPC):	2.5
MFR E (ASTM D 1238):	1.0 g/10 min
F/E (ASTM D 1238):	16
Soluble in xylene at 25°C (wt%):	1

B) Crystalline Propylene Copolymer

The propylene copolymers B1)-B3), having the following characteristics, are used:

	B1)	B2)	B3)
Butene content (wt%):	5.3	--	--
Ethylene content (wt%):	2.21	3.3	3.3
Density (g/cm ³):	0.895	0.898	0.898
MFR L (g/10 min):	6	2	9
Soluble in xylene at 25°C (wt%):	10	7	7

The aforesaid butene and ethylene contents are measured by IR spectroscopy, the density by ASTM D 4883, and the content of insoluble in xylene (and hence the content of soluble), both for the component A) and for the component B), is determined by the following method.

2.5 g of copolymer together with 250 cm³ of o-xylene are placed in a conical glass flask, equipped with condenser

and magnetic stirrer. The temperature is raised until the boiling point of the solvent is reached in 30 min. The clear solution thus formed is left at reflux with stirring for another 30 min. The closed flask is then placed in a bath of water and ice for 30 min and then in a bath of water thermostatted at 25°C for 30 min. The solid formed is filtered on paper at a high filtration rate. 100 cm³ of the liquid obtained from the filtration are poured into an aluminium container, previously weighed, and the whole is placed on a heating plate to evaporate the liquid in a current of nitrogen. The container is then placed in an oven at 80°C and kept under vacuum until constant weight is attained.

The aforesaid propylene copolymers are prepared using high yield and stereospecificity Ziegler-Natta catalysts, supported on magnesium chloride, in the polymerization.

C) LDPE Polymer

A homopolymer of ethylene prepared by polymerization in the presence of free radical initiators, having density values of 0.919 g/cm³ (measured according to ASTM D 4883) and MFR E values of 0.3 g/10 min (ASTM D 1238).

Examples 1-5

The aforesaid components A), B1)-B3) and C) are mixed in the melted state in a single-screw extruder (Bandera TR-60) under the following conditions:

Temperature profile: 185, 195, 200, 205, 210, 215, 235,

melted 230°C;
 Screw revolutions: 70 rpm;
 Throughput: 67 kg/h.

The relative quantities (% by weight) relative to the total weight of the composition) of the aforesaid components for each example are shown below.

Example No.	1	2	3	4	5
A)	80	80	80	70	77.68
B1)	20	--	--	--	19.42
B2)	--	20	--	30	--
B3)	--	--	20	--	--
C)	--	--	--	--	2.9

From the compositions thus obtained, blown films of 25 μ m thickness are prepared using a COLLIN-25 machine under the following conditions:

Temperature profile: 155, 165, 175, 185, 190, 190, 190, 190, melted 200°C;
 Screw revolutions: 90 rpm;
 Throughput: 4.2 kg/h;
 Blow-up ratio: 2.5.

For each example, the properties set out in Table 1 are measured on the films thus prepared. For comparison purposes, Table 1 also shows the properties of blown films obtained and subjected to testing under the same conditions as

in examples 1-5, but using the component A) in the pure state (reference example 1) or an LLDPE copolymer in the pure state, containing 10.5% by weight of 1-octene and having the following characteristics (reference example 2):

Density: 0.9175 g/cm³;
 $\overline{M}_w/\overline{M}_n$: 5
 MFR E: 1.00 g/10 min;
 F/E: 31.

Table 1

Ex. No.	1	2	3	4	5	Ref.1	Ref.2
Head pressure (MPa)	22	26	19.5	21	19.7	27	26
Motor input (A)	8.8	9.0	8.2	8.5	9.1	9.3	8.1
Haze (%)	28	33	27	27	6	30	19
Gloss (%)	22	24	25	27	65	25	39
Dart Test (g)	560	375	365	330	390	860	270
Elmendorf							
TD (g)	570	450	490	435	645	330	600
MD (g)	350	240	320	245	295	310	370

With reference to Table 1, the head pressure corresponds to the pressure measured at the head of the

extruder while the number of revolutions of the motor relate to the extruder motor.

Further, the properties of the films shown in Table 1 are measured by the following standard ASTM methods:

Haze:	ASTM D 1003
Gloss:	ASTM D 2457
Dart Test:	ASTM D 1709
Elmendorf:	ASTM D 1922.

CLAIMS

1. Polyethylene composition comprising (percentages by weight):
 - A) from 60 to 95% of a copolymer of ethylene with an alpha-olefin $\text{CH}_2=\text{CHR}$, wherein R is an alkyl radical containing from 1 to 18 atoms of carbon, (LLDPE copolymer), the said copolymer having a density from 0.905 to 0.935 g/cm³, $\overline{M}_w/\overline{M}_n$ values less than 4, and values of melt flow rate F/E ratio from 10 to 20;
 - B) from 5 to 40% of one or more crystalline copolymers of propylene selected among (i) copolymers of propylene with ethylene containing from 3 to 8% of ethylene; (ii) copolymers of propylene with one or more alpha-olefins $\text{CH}_2=\text{CHR}^I$, where R^I is an alkyl radical having from 2 to 8 carbon atoms or an aryl radical, containing from 6 to 25% of alpha-olefins $\text{CH}_2=\text{CHR}^I$; (iii), copolymers of propylene with ethylene and one or more alpha-olefins $\text{CH}_2=\text{CHR}^I$, where R^I has the aforesaid meaning, containing from 0.1 to 8% of ethylene and from 0.1 to 20% of alpha-olefins $\text{CH}_2=\text{CHR}^I$, with proviso that the total content of ethylene and alpha-olefins $\text{CH}_2=\text{CHR}^I$ in the copolymers (iii) is greater than or equal to 5%.
2. The polyethylene composition of Claim 1 comprising, in addition, from 0.5 to 10% by weight of LDPE polyethylene (component C)), with respect to the total weight of

A)+B)+C).

3. The polyethylene composition of Claim 1, wherein the component B) has a density less than 0.900 g/cm^3 .
4. The polyethylene composition of Claim 1, wherein the fraction of the component B) that is insoluble in xylene at 25°C is greater than 70% by weight.
5. The polyethylene composition of Claim 1, having Dart Test values, measured on blown film of thickness $25 \text{ }\mu\text{m}$ according to ASTM D 1709, greater than or equal to 300 g.
6. Mono- or multilayer film, wherein at least one layer comprises the polyethylene composition of Claim 1.
7. Blown film according to Claim 6.

INTERNATIONAL SEARCH REPORT

Internat Application No

PCT/EP 99/04597

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08L23/08 //(C08L23/08,C08L23:14)

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 871 813 A (SENEZ ALAIN) 3 October 1989 (1989-10-03) cited in the application column 1, line 46 -column 3, line 35 claim 1; examples 1,4,5	1,6,7
X	WO 92 14784 A (MEHTA, ASPY, KEKI) 3 September 1992 (1992-09-03) page 23; table II page 24, line 20 - line 31; examples 3,5,7 page 30, line 14 - line 35; tables II,V	1,6,7
Y	US 5 455 303 A (PANAGOPOULOS JR GEORGE ET AL) 3 October 1995 (1995-10-03) column 2, line 10 -column 3, line 63; examples 4,5; tables 1,4	1-7
	-/--	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

30 September 1999

Date of mailing of the international search report

22/10/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Parry, J

INTERNATIONAL SEARCH REPORT

Intern Application No

PCT/EP 99/04597

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	<p>WO 97 48554 A (MERGENHAGEN LAURA K ;CHUM PAK WING S (US); DOW CHEMICAL CO (US); P) 24 December 1997 (1997-12-24) page 2, paragraph 7 -page 3, paragraph 2 claim 2 page 4, paragraph 3 -page 5, paragraph 3 page 6, paragraph 2 - paragraph 5; tables I,II,III</p> <p style="text-align: center;">-----</p>	1-2

INTERNATIONAL SEARCH REPORT
Information on patent family members

International Application No
PCT/EP 99/04597

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4871813 A	03-10-1989	FR 2603291 A	04-03-1988
		AT 101177 T	15-02-1994
		DE 3788989 D	17-03-1994
		DE 3788989 T	19-05-1994
		EP 0260038 A	16-03-1988
		JP 63132951 A	04-06-1988
WO 9214784 A	03-09-1992	CA 2103790 A	23-08-1992
		DE 69219117 D	22-05-1997
		DE 69219117 T	30-10-1997
		EP 0575465 A	29-12-1993
		ES 2101838 T	16-07-1997
		JP 6504808 T	02-06-1994
		MX 9200724 A	01-05-1993
		US 5358792 A	25-10-1994
US 5455303 A	03-10-1995	AT 172221 T	15-10-1998
		AU 689876 B	09-04-1998
		AU 2178695 A	04-01-1996
		BR 9502862 A	30-04-1996
		CA 2152157 A	21-12-1995
		CN 1118361 A	13-03-1996
		DE 69505311 D	19-11-1998
		DE 69505311 T	08-04-1999
		EP 0688820 A	27-12-1995
		ES 2125520 T	01-03-1999
		FI 953046 A	21-12-1995
		JP 8003385 A	09-01-1996
		NO 952446 A	21-12-1995
WO 9748554 A	24-12-1997	AU 3403097 A	07-01-1998